

Distributed by:

**JAMECO**<sup>®</sup>  
ELECTRONICS

**www.Jameco.com ♦ 1-800-831-4242**


The content and copyrights of the attached  
material are the property of its owner.

Jameco Part Number 736124

# C0G (NP0) Dielectric



## General Specifications



C0G (NP0) is the most popular formulation of the “temperature-compensating,” EIA Class I ceramic materials. Modern C0G (NP0) formulations contain neodymium, samarium and other rare earth oxides.

C0G (NP0) ceramics offer one of the most stable capacitor dielectrics available. Capacitance change with temperature is  $0 \pm 30 \text{ ppm}/^\circ\text{C}$  which is less than  $\pm 0.3\% \Delta C$  from  $-55^\circ\text{C}$  to  $+125^\circ\text{C}$ . Capacitance drift or hysteresis for C0G (NP0) ceramics is negligible at less than  $\pm 0.05\%$  versus up to  $\pm 2\%$  for films. Typical capacitance change with life is less than  $\pm 0.1\%$  for C0G (NP0), one-fifth that shown by most other dielectrics. C0G (NP0) formulations show no aging characteristics.

## PART NUMBER (see page 2 for complete part number explanation)

**0805**

**Size**  
(L" x W")

**5**

**Voltage**  
6.3V = 6  
10V = Z  
16V = Y  
25V = 3  
50V = 5  
100V = 1  
200V = 2  
500V = 7

**A**

**Dielectric**  
C0G (NP0) = A

**101**

**Capacitance Code (In pF)**  
2 Sig. Digits +  
Number of  
Zeros

**J**

**Capacitance Tolerance**  
B =  $\pm 10 \text{ pF}$  ( $< 10 \text{ pF}$ )  
C =  $\pm 25 \text{ pF}$  ( $< 10 \text{ pF}$ )  
D =  $\pm 50 \text{ pF}$  ( $< 10 \text{ pF}$ )  
F =  $\pm 1\%$  ( $\geq 10 \text{ pF}$ )  
G =  $\pm 2\%$  ( $\geq 10 \text{ pF}$ )  
J =  $\pm 5\%$   
K =  $\pm 10\%$

**A**

**Failure Rate**  
A = Not  
Applicable

**T**

**Terminations**  
T = Plated Ni  
and Sn  
7 = Gold Plated

**2**

**Packaging**  
2 = 7" Reel  
4 = 13" Reel  
7 = Bulk Cass.  
9 = Bulk

**A**


**Special Code**  
A = Std.  
Product

**Contact Factory For**  
1 = Pd/Ag Term


**Contact Factory For**  
Multiples

NOTE: Contact factory for availability of Termination and Tolerance Options for Specific Part Numbers.  
Contact factory for non-specified capacitance values.


**Temperature Coefficient**




**Δ Capacitance vs. Frequency**




**Insulation Resistance vs Temperature**




**Variation of Impedance with Cap Value**  
Impedance vs. Frequency  
0805 - C0G (NP0)  
10 pF vs. 100 pF vs. 1000 pF



**Variation of Impedance with Chip Size**  
Impedance vs. Frequency  
1000 pF - C0G (NP0)




**Variation of Impedance with Ceramic Formulation**  
Impedance vs. Frequency  
1000 pF - C0G (NP0) vs X7R  
0805



# COG (NP0) Dielectric



## Specifications and Test Methods

Parameter/Test		NP0 Specification Limits	Measuring Conditions	
Operating Temperature Range		-55°C to +125°C	Temperature Cycle Chamber	
Capacitance		Within specified tolerance	Freq.: 1.0 MHz $\pm$ 10% for cap $\leq$ 1000 pF 1.0 kHz $\pm$ 10% for cap > 1000 pF Voltage: 1.0Vrms $\pm$ .2V	
Q		<30 pF: Q $\geq$ 400+20 x Cap Value $\geq$ 30 pF: Q $\geq$ 1000		
Insulation Resistance		100,000M $\Omega$ or 1000M $\Omega$ - $\mu$ F, whichever is less	Charge device with rated voltage for 60 $\pm$ 5 secs @ room temp/humidity	
Dielectric Strength		No breakdown or visual defects	Charge device with 300% of rated voltage for 1-5 seconds, w/charge and discharge current limited to 50 mA (max) Note: Charge device with 150% of rated voltage for 500V devices.	
Resistance to Flexure Stresses	Appearance	No defects	Deflection: 2mm Test Time: 30 seconds 	
	Capacitance Variation	$\pm$ 5% or $\pm$ .5 pF, whichever is greater		
	Q	Meets Initial Values (As Above)		
	Insulation Resistance	$\geq$ Initial Value x 0.3		
Solderability		$\geq$ 95% of each terminal should be covered with fresh solder	Dip device in eutectic solder at 230 $\pm$ 5°C for 5.0 $\pm$ 0.5 seconds	
Resistance to Solder Heat	Appearance	No defects, <25% leaching of either end terminal	Dip device in eutectic solder at 260°C for 60 seconds. Store at room temperature for 24 $\pm$ 2 hours before measuring electrical properties.	
	Capacitance Variation	$\leq$ $\pm$ 2.5% or $\pm$ .25 pF, whichever is greater		
	Q	Meets Initial Values (As Above)		
	Insulation Resistance	Meets Initial Values (As Above)		
Thermal Shock	Dielectric Strength	Meets Initial Values (As Above)	Step 1: -55°C $\pm$ 2°     30 $\pm$ 3 minutes	
	Appearance	No visual defects	Step 2: Room Temp $\leq$ 3 minutes	
	Capacitance Variation	$\leq$ $\pm$ 2.5% or $\pm$ .25 pF, whichever is greater	Step 3: +125°C $\pm$ 2°     30 $\pm$ 3 minutes	
	Q	Meets Initial Values (As Above)	Step 4: Room Temp $\leq$ 3 minutes	
	Insulation Resistance	Meets Initial Values (As Above)	Repeat for 5 cycles and measure after 24 hours at room temperature	
Load Life	Dielectric Strength	Meets Initial Values (As Above)	Charge device with twice rated voltage in test chamber set at 125°C $\pm$ 2°C for 1000 hours (+48, -0).  Remove from test chamber and stabilize at room temperature for 24 hours before measuring.	
	Appearance	No visual defects		
	Capacitance Variation	$\leq$ $\pm$ 3.0% or $\pm$ .3 pF, whichever is greater		
	Q (C=Nominal Cap)	$\geq$ 30 pF: Q $\geq$ 350 $\geq$ 10 pF, <30 pF: Q $\geq$ 275 +5C/2 <10 pF: Q $\geq$ 200 +10C		
Load Humidity	Insulation Resistance	$\geq$ Initial Value x 0.3 (See Above)	Store in a test chamber set at 85°C $\pm$ 2°C/ 85% $\pm$ 5% relative humidity for 1000 hours (+48, -0) with rated voltage applied.  Remove from chamber and stabilize at room temperature for 24 $\pm$ 2 hours before measuring.	
	Dielectric Strength	Meets Initial Values (As Above)		
	Appearance	No visual defects		
	Capacitance Variation	$\leq$ $\pm$ 5.0% or $\pm$ .5 pF, whichever is greater		
Load Humidity	Q	$\geq$ 30 pF: Q $\geq$ 350 $\geq$ 10 pF, <30 pF: Q $\geq$ 275 +5C/2 <10 pF: Q $\geq$ 200 +10C		
	Insulation Resistance	$\geq$ Initial Value x 0.3 (See Above)		
	Dielectric Strength	Meets Initial Values (As Above)		
	Appearance	No visual defects		


# COG (NP0) Dielectric



## Capacitance Range

PREFERRED SIZES ARE SHADED

SIZE		0201			0402			0603			0805				1206							
Soldering		Reflow Only			Reflow Only			Reflow Only			Reflow/Wave				Reflow/Wave							
Packaging		All Paper			All Paper			All Paper			Paper/Embossed				Paper/Embossed							
(L) Length	MM (in.)	0.60 ± 0.03 (0.024 ± 0.001)			1.00 ± 0.10 (0.040 ± 0.004)			1.60 ± 0.15 (0.063 ± 0.006)			2.01 ± 0.20 (0.079 ± 0.008)				3.20 ± 0.20 (0.126 ± 0.008)							
(W) Width	MM (in.)	0.30 ± 0.03 (0.011 ± 0.001)			0.50 ± 0.10 (0.020 ± 0.004)			0.81 ± 0.15 (0.032 ± 0.006)			1.25 ± 0.20 (0.049 ± 0.008)				1.60 ± 0.20 (0.063 ± 0.008)							
(t) Terminal	MM (in.)	0.15 ± 0.05 (0.006 ± 0.002)			0.25 ± 0.15 (0.010 ± 0.006)			0.35 ± 0.15 (0.014 ± 0.006)			0.50 ± 0.25 (0.020 ± 0.010)				0.50 ± 0.25 (0.020 ± 0.010)							
WVDC		25	50	16	25	50	16	25	50	100	16	25	50	100	200	16	25	50	100	200	500	
Cap (pF)	0.5	A	C	C	C	C	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J	
	1.0	A	C	C	C	C	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J	
	1.2	A	C	C	C	C	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J	
	1.5	A	A	C	C	C	C	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J
	1.8	A	A	C	C	C	C	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J
2.2	A	A	C	C	C	C	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J	
2.7	A	A	C	C	C	C	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J	
3.3	A	A	C	C	C	C	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J	
3.9	A	A	C	C	C	C	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J	
4.7	A	A	C	C	C	C	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J	
5.6	A	A	C	C	C	C	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J	
6.8	A	A	C	C	C	C	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J	
8.2	A	A	C	C	C	C	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J	
10	A	A	C	C	C	C	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J	
12	A	A	C	C	C	C	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J	
15	A	A	C	C	C	C	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J	
18	A	A	C	C	C	C	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J	
22	A	A	C	C	C	C	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J	
27	A	A	C	C	C	C	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J	
33	A	A	C	C	C	C	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J	
39	A	A	C	C	C	C	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J	
47	A	A	C	C	C	C	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J	
56	A	A	C	C	C	C	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J	
68	A	A	C	C	C	C	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J	
82	A	A	C	C	C	C	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J	
100	A	A	C	C	C	C	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J	
120	A	A	C	C	C	C	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J	
150	A	A	C	C	C	C	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J	
180	A	A	C	C	C	C	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J	
220	A	A	C	C	C	C	G	G	G	G	J	J	J	J	J	J	J	J	J	J	J	
270	A	A	C	C	C	C	G	G	G	G	J	J	J	J	M	J	J	J	J	J	M	
330	A	A	C	C	C	C	G	G	G	G	J	J	J	J	M	J	J	J	J	J	M	
390	A	A	C	C	C	C	G	G	G	G	J	J	J	J	M	J	J	J	J	J	M	
470	A	A	C	C	C	C	G	G	G	G	J	J	J	J	M	J	J	J	J	J	M	
560	A	A	C	C	C	C	G	G	G	G	J	J	J	J	M	J	J	J	J	J	M	
680	A	A	C	C	C	C	G	G	G	G	J	J	J	J	M	J	J	J	J	J	M	
820	A	A	C	C	C	C	G	G	G	G	J	J	J	J	M	J	J	J	J	J	M	
1000	A	A	C	C	C	C	G	G	G	G	J	J	J	J	M	J	J	J	J	J	Q	
1200	A	A	C	C	C	C	G	G	G	G	J	J	J	J	M	J	J	J	J	J	Q	
1500	A	A	C	C	C	C	G	G	G	G	J	J	J	J	M	J	J	J	J	J	Q	
1800	A	A	C	C	C	C	G	G	G	G	J	J	J	J	M	J	J	M	M	M		
2200	A	A	C	C	C	C	G	G	G	G	J	J	J	N	M	J	J	M	P	P		
2700	A	A	C	C	C	C	G	G	G	G	J	J	J	N	M	J	J	M	P	P		
3300	A	A	C	C	C	C	G	G	G	G	J	J	J		M	J	J	M	P	P		
3900	A	A	C	C	C	C	G	G	G	G	J	J	J		M	J	J	M	P	P		
4700	A	A	C	C	C	C	G	G	G	G	J	J	J		M	J	J	M	P	P		
5600	A	A	C	C	C	C	G	G	G	G	J	J	J		M	J	J	M				
6800	A	A	C	C	C	C	G	G	G	G	J	J	J		M	J	J	M				
8200	A	A	C	C	C	C	G	G	G	G	J	J	J		M	J	J	M				
Cap (µF)																M	M	M				
0.010																M	M	M				
0.012																M	M	M				
0.015																M	M	M				
0.018																						
0.022																						
0.027																						
0.033																						
0.039																						
0.047																						
0.068																						
0.082																						
0.1																						
WVDC		25	50	16	25	50	16	25	50	100	16	25	50	100	200	16	25	50	100	200	500	
SIZE		0201			0402			0603			0805				1206							
Letter		A	C	E	G	J	K	M	N	P	Q	X	Y	Z								
Max. Thickness		0.33 (0.013)	0.56 (0.022)	0.71 (0.028)	0.90 (0.035)	0.94 (0.037)	1.02 (0.040)	1.27 (0.050)	1.40 (0.055)	1.52 (0.060)	1.78 (0.070)	2.29 (0.090)	2.54 (0.100)	2.79 (0.110)								
		PAPER						EMBOSS														



# COG (NP0) Dielectric



## Capacitance Range

PREFERRED SIZES ARE SHADED

SIZE		1210					1812					1825					2220					2225				
Soldering		Reflow Only					Reflow Only					Reflow Only					Reflow Only					Reflow Only				
Packaging		Paper/Embossed					All Embossed					All Embossed					All Embossed					All Embossed				
(L) Length	MM (in.)	3.20 ± 0.20 (0.126 ± 0.008)					4.50 ± 0.30 (0.177 ± 0.012)					4.50 ± 0.30 (0.177 ± 0.012)					5.70 ± 0.40 (0.225 ± 0.016)					5.72 ± 0.25 (0.225 ± 0.010)				
(W) Width	MM (in.)	2.50 ± 0.20 (0.098 ± 0.008)					3.20 ± 0.20 (0.126 ± 0.008)					6.40 ± 0.40 (0.252 ± 0.016)					5.00 ± 0.40 (0.197 ± 0.016)					6.35 ± 0.25 (0.250 ± 0.010)				
(t) Terminal	MM (in.)	0.50 ± 0.25 (0.020 ± 0.010)					0.61 ± 0.36 (0.024 ± 0.014)					0.61 ± 0.36 (0.024 ± 0.014)					0.64 ± 0.39 (0.025 ± 0.015)					0.64 ± 0.39 (0.025 ± 0.015)				
Cap	MM (in.)																									
Cap	(pF)																									
Cap	(μF)																									
0.5																										
1.0																										
1.2																										
1.5																										
1.8																										
2.2																										
2.7																										
3.3																										
3.9																										
4.7																										
5.6																										
6.8																										
8.2																										
10						J																				
12						J																				
15						J																				
18						J																				
22						J																				
27						J																				
33						J																				
39						J																				
47						J																				
56						J																				
68						J																				
82						J																				
100						J																				
120						J																				
150						J																				
180						J																				
220						J																				
270						J																				
330						J																				
390						M																				
470						M																				
560		J	J	J	J	M																				
680		J	J	J	J	M																				
820		J	J	J	J	M																				
1000		J	J	J	J	M	K	K	K	K	M	M	M	M	M						M	M	M	P	P	
1200		J	J	J	M	M	K	K	K	K	M	M	M	M	M						M	M	M	P	P	
1500		J	J	J	M	M	K	K	K	K	M	M	M	M	M						M	M	M	P	P	
1800		J	J	J	M		K	K	K	K	M	M	M	M	M						M	M	M	P	P	
2200		J	J	J	Q		K	K	K	K	P	M	M	M	M						M	M	M	P	P	
2700		J	J	J	Q		K	K	K	P	Q	M	M	M						M	M	M	P	P		
3300		J	J	J			K	K	K	P	Q	M	M	M				X		M	M	M	P	P		
3900		J	J	M			K	K	K	P	Q	M	M	M				X		M	M	M	P	P		
4700		J	J	M			K	K	K	P	Q	M	M	M				X	X	M	M	M	P	P		
5600		J	J				K	K	M	P	X	M	M	M				X	X	M	M	M	P	P		
6800		J	J				K	K	M	X		M	M	M				X	X	M	M	M	P	P		
8200		J	J				K	M	M			M	M	M				X	X	M	M	M	P	P		
Cap	(pF)	J	J				K	M	M			M	M	M				X	X	M	M	M	P	P		
0.010		J	J				K	M	M			M	M	M				X	X	M	M	M	P	P		
0.012		J	J				K	M	M			M	M	M				X	X	M	M	M	P	P		
0.015							M	M	M			M	M	M				X	X	M	M	M	Y	Y		
0.018							M	M	M			P	M					X	X	M	M	M	Y	Y		
0.022							M	M	M			P						X	X	M	M	M	Y	Y		
0.027							M	M	M			P						X	X	M	M	M	Y	Y		
0.033							M	M	M			P						X	X	M	M	M	Y	Y		
0.039							M	M	M			P						Y		M	M	M	Y	Y		
0.047							M	M	M			P						Y		M	M	M	Y	Y		
0.068							M	M	M											M	M	M	Y	Y		
0.082							M	M	M											M	M	M	Y	Y		
0.1							M	M	M											M	M	M	Y	Y		
WVDC		25	50	100	200	500	25	50	100	200	500	50	100	200	50	100	200	50	100	200	50	100	200			
SIZE		1210					1812					1825					2220					2225				
Letter		A	C	E	G	J	K	M	N	P	Q	X	Y	Z												
Max. Thickness		0.33 (0.013)	0.56 (0.022)	0.71 (0.028)	0.90 (0.035)	0.94 (0.037)	1.02 (0.040)	1.27 (0.050)	1.40 (0.055)	1.52 (0.060)	1.78 (0.070)	2.29 (0.090)	2.54 (0.100)	2.79 (0.110)												
		PAPER					EMBOSS																			

